

I claim:

- Sub G1
5
1. A fiber optic cable, comprising:
an outer layer;
at least one optical fiber disposed inside said outer layer; and
a gel-swellaible portion and water resistant gel positioned adjacent to each other and
disposed between said outer layer and said optical fiber;
wherein said gel-swellaible portion absorbs at least some of said gel.
 2. The fiber optic cable according to claim 1, wherein said gel-swellaible portion
is a continuous layer surrounding said at least one optical fiber.
 3. The fiber optic cable according to claim 2, wherein said continuous layer has
an uneven thickness.
 4. The fiber optic cable according to claim 1, wherein said at least one gel
swellaible portion has a smooth surface.
 5. The fiber optic cable according to claim 1, wherein said at least one gel-
swellaible portion is adhered to an outer surface of said at least one optical fiber.
 6. The fiber optic cable according to claim 1, wherein said at least one gel-
swellaible portion is adhered to an inner surface of said outer layer.
- Sub B2
15
20

7. The fiber optic cable according to claim 1, wherein said at least one gel-swellable portion extends longitudinally along the length of said at least one optical fiber.

8. The fiber optic cable according to claim 1, wherein said at least one gel-swellable portion has an uneven thickness.

9. The fiber optic cable according to claim 1, wherein said gel-swellable portion has a density less than 0.90 g/cc.

10. The fiber optic cable according to claim 1, wherein said gel-swellable portion is one of a copolymer or terpolymer of polyethelene.

11. The fiber optic cable according to claim 1, wherein said gel-swellable portion swells more than 10% at 85°C.

12. The fiber optic cable according to claim 1, wherein said gel is a polyolefin oil based gel.

13. The fiber optic cable according to claim 1, wherein said gel-swellable portion is a polyolefin swellable material.

14. The fiber optic cable according to claim 1, wherein said gel-swella-
ble portion is softer than said outer layer.

Sub 5 A2 →
15. A fiber optic cable, comprising:
an outer layer;
at least one optical fiber ribbon disposed inside said outer layer; and
a gel-swella-
ble layer and a water resistant gel positioned adjacent to each other and
disposed between said outer layer and said ribbon;
wherein said gel swella-
ble layer absorbs at least some of a said gel.

Sub 6 B5 →
16. The fiber optic cable according to claim 15, wherein said gel-swella-
ble portion is a continuous layer surrounding said at least one ribbon.

15 17. The fiber optic cable according to claim 16, wherein said continuous layer has
an uneven thickness.

18. The fiber optic cable according to claim 15, wherein said at least one gel-
swella-
ble portion has a smooth surface.

20 19. The fiber optic cable according to claim 15, wherein said at least one gel-
swella-
ble portion is secured to an outer surface of said at least one ribbon.

20. The fiber optic cable according to claim 15, wherein said at least one gel-swella-
ble portion is secured to an inner surface of said outer layer.

21. The fiber optic cable according to claim 15, wherein said at least one gel-
5 swella-ble portion extends longitudinally along the length of said at least one ribbon.

22. The fiber optic cable according to claim 15, wherein said at least one gel-
swella-ble portion has an uneven thickness.

23. The fiber optic cable according to claim 15, wherein said gel-swella-ble layer
has a density less than 0.90 g/cc.

24. The fiber optic cable according to claim 15, wherein said gel-swella-ble layer is
one of a copolymer or terpolymer of polyethylene.

25. The fiber optic cable according to claim 1, wherein said gel-swella-ble layer
swells more than 10% at 85°C.

26. The fiber optic cable according to claim 15, wherein said gel is a polyolefin oil
20 based gel.

27. The fiber optic cable according to claim 15, wherein said gel-swella-ble layer is
a polyolefin swella-ble material.

Sub Bc

09851247.05090115

28. The fiber optic cable according to claim 15, wherein said gel-swellable portion is softer than said outer layer.

5
Sub A3
29. A fiber optic cable, comprising:
an outer layer, having at least one gel-swellable portion adhered to an inside surface of said outer layer;
at least one optical fiber; and
a water resistant gel disposed between said at least one optical fiber and said outer layer;
wherein said gel-swellable portion absorbs at least some of said gel.

15
Sub B8
30. The fiber optic cable according to claim 29, wherein said gel-swellable portion is a continuous layer on said inner surface of said outer layer.

31. The fiber optic cable according to claim 30, wherein said continuous layer has an uneven thickness.

20
32. The fiber optic cable according to claim 29, wherein said at least one gel-swellable portion has a smooth surface.

33. The fiber optic cable according to claim 29, further comprising at least one other gel-swellable portion adhered to an outer surface of said at least one optical fiber.

34. The fiber optic cable according to claim 29, wherein said at least one gel-swellable portion extends longitudinally along the length of said outer layer.

5 35. The fiber optic cable according to claim 29, wherein said at least one gel-swellable portion has an uneven thickness.

36. The fiber optic cable according to claim 29, wherein said gel-swellable portion has a density less than 0.90 g/cc.

37. The fiber optic cable according to claim 29, wherein said gel-swellable portion is one of a copolymer or terpolymer of polyethelene.

38. The fiber optic cable according to claim 29, wherein said gel-swellable portion swells more than 10% at 85°C.

39. The fiber optic cable according to claim 29, wherein said gel is a polyolefin oil based gel.

40. The fiber optic cable according to claim 29, wherein said gel-swellable portion is a polyolefin swellable material.

U.S. Patent Application

Inventors: Mike Rossi, Nicholas V. Nechitailo and Brian Risch

Our Ref.: A7966

41. The fiber optic cable according to claim 29, wherein said gel-swella-
ble portion is softer than said outer layer.

5

Add B11

Add B11

09851247 050901